# Station Road, Topcliffe, Thirsk, North Yorkshire, Y07 3SE, United kingdom Email: info@resimac.co.uk

# www.resimacsolutions.com

Tel: +44(0) 1845 577498

Resimac Ltd, Unit B, Park Barn Estate,

# resimac Ltd.

# 106 Metal Repair Paste XF

Fast curing solvent free epoxy repair paste Applied at 20mm without slumping Fully machineable once cured

## **Cure Times**

At 20°C (68F°) the product will have the following cure times – **Usable Life** 5mins

Touch dry 45mins Machining / light loading

2 hours

Full cure 1 day

# **Coverage Rates**

500gm (1.1lb) of fully mixed product will give the following coverage rates -0.277m<sup>2</sup> at 1mm 3ft<sup>2</sup> at 40mil 0.139m<sup>2</sup> at 2mm 1.5ft<sup>2</sup> at 80mil 0.092m<sup>2</sup> at 3mm 1ft<sup>2</sup> at 1/8"

## Colour

Mixed material – Light Grev Base component – Black Activator component -White

# **Over-coating times**

Minimum - as soon as it is touch dry.

Maximum - the over-coating time should not exceed 3 hours.

**Typical Applications** Damaged pump shafts Cracked pump or valve casings **Damaged flanges** Leaking tank seams **Cracked engine blocks Plate Bonding** 

# **Technical specifications and characteristics**

Mixing ratios By weight 1 to 1

By volume Volume capacity Metric 278cc/500gm

> Imperial 16.8cu in/1.1lb

1 to 1

# **Surface Preparation**

Ideal surface preparation for this material is abrasive blast cleaning to ISO 8501/4 Standard SA2.5 (SSPC SP10/ NACE 2) and with a minimum blast profile of 75 microns using an angular abrasive.

However this product has been designed for surfaces with less than ideal surface preparation -

Hand tools, use a wire brush or coarse sand paper to abrade the surface. Mechanical tools, use a handheld mechanical grinder with a coarse grinding pad or rotary wire brush. DO NOT POLISH THE SURFACE, ENSURE THAT THE SURFACE HAS A CROSS HATCH PATTERN.

MBX bristle blaster. for the best mechanical surface preparation results use an MBX bristle blaster. Ensure all loose material and as much surface contamination is cleaned from the surface.

Ensure the repair surface is wiped with an appropriate solvent cleaner such as MEK after abrading the surface.

# **Mixing and Application**

### STEP 1

Ensure you have 1 x base unit, 1 x activator unit, 1 x spatula, 1 applicator, 1 x clean mixing area.



### STEP 2

Take equal measures of base and activator materials, ensure the spatula is clean.



### STEP 3

Mix the two components using the spatula provided, ensure any unmixed material around the edges is mixed.



### STEP 4

To ensure the product is fully mixed create a diamond pattern on the surface and look for any areas which are not mid grey in colour.



### STEP 5

Once the material is fully mixed use the applicator tool provided to apply the metal repair paste to the surface

